

RTM C60

Cassette Pancakes

RTM C60 Cassette Pancakes

BASED ON LEGENDARY SM900 FORMULA


WIDTH: 3.81MM

MINIMAL PRINT-THROUGH

TYPE ONE, NORMAL BIAS

PRODUCED FROM 2018 ONWARDS

MADE IN FRANCE




RTM C60 Cassette Pancakes

Technical Data

	Parameters	C60 pancake data	Notes
General Properties	Maximum recording time once loaded	60 min	
	Tape width	3.81 mm (+0.00/-0.05)	
	Tape length	3300m	
	Average diameter	27.5cm	
Physical Properties	Coating thickness	5 $\mu\text{m} \pm 0.5 \mu\text{m}$	
	Base film thickness	12 $\mu\text{m} \pm 0.5 \mu\text{m}$	Polyester
	Total Thickness	17 $\pm 1 \mu\text{m}$	
	Yield Strength (3%)	$\geq 5 \text{ N}$	
	Breaking Strength	$\geq 9 \text{ N}$	
	Electrical resistance of magnetic coating	$\leq 4 \text{ G}\Omega$	
Magnetic Properties	Coercivity	370 Oe	Ferric Oxide (Fe2O3)
	Saturation retentivity	1500 G	
Electrical properties	Sensitivity at 315Hz	-0.6 dB	Compared to IEC I tape
	Sensitivity at 10kHz	+0.5 dB	Compared to IEC I tape
	Maximum output level at 315Hz (MOL)	+2.2 dB	dB above reference level of 250 nWb/m
	Saturated output level at 10kHz (SOL)	-6 dB	Relative to reference level
	Bias noise	+0.6 dB	Compared to IEC I tape
	Audio S/N ratio	More than 48 dB	

All data given in the specification are subject to change without prior notice due to technical progress

RTM C60 Cassette Pancakes



53 rue Division Leclerc
50300 Avranches
www.recordingthemasters.com